

AD-A152 290

ION AND POLYMER CHAIN MOTION IN A SUPERIONIC
SODIUM-POLY(ETHYLENE OXIDE)... (U) HUNTER COLL NEW YORK
DEPT OF PHYSICS AND ASTRONOMY S G GREENBAUM ET AL
NOV 85 TR-3 N00014-84-K-0010


1/1

UNCLASSIFIED

F/G 7/4

NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS 1963-A

AD-A152 290

OFFICE OF NAVAL RESEARCH

Contract N00014-84K-0010

Task No. NR 359-841

Technical Report No. 3

ION AND POLYMER CHAIN MOTION IN A SUPERIONIC
SODIUM-POLY(ETHYLENE OXIDE) COMPLEX

by

S.G. Greenbaum and A.N. Shetty

Prepared for Publication

in

Solid State Ionics

March 1985

Hunter College of CUNY
Department of Physics
New York, N.Y. 10021

DTIC
ELECTE

APR 03 1985

E

Reproduction in whole or in part is permitted for any purpose of the
United States Government.

Approved
Date 12/1/84

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 3	2. GOVT ACCESSION NO. AD-A152290	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) ION AND POLYMER CHAIN MOTION IN A SUPERIONIC SODIUM-POLY(ETHYLENE OXIDE) COMPLEX		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) S.G. Greenbaum and A.N. Shetty		8. CONTRACT OR GRANT NUMBER(s) N00014-84K-0010
9. PERFORMING ORGANIZATION NAME AND ADDRESS Hunter College of CUNY Department of Physics and Astronomy New York, N.Y. 10021		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research/Code 413 800 N. Quincy Street Arlington, VA 22217		12. REPORT DATE March 1985
		13. NUMBER OF PAGES 14
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release and sale. Distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES The paper will appear in Solid State Ionics.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Solid electrolytes, poly(ethylene oxide), molecular motion, NMR, EPR,		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Magnetic resonance measurements have been performed on the ion conducting complex poly(ethylene oxide) _{4.5} NaClO ₄ . Low temperature ²³ Na NMR spectra suggest a highly symmetric environment for the Na-ions as evidenced by the absence of quadrupole broadening. Proton spin-lattice relaxation measurements provide an estimate of 4×10^{-10} sec for the polymer chain motional correlation time at T=69C. Correlation times of tumbling paramagnetic probe molecule have been extracted from EPR spectra of ¹⁵ N-enriched TANOL-doped complex. Changes in polymer chain mobility above T=120C are inferred from the results and may be consistent with previous scanning calorimetry measurements.		

DD FORM 14/3

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF 014-6601

ION AND POLYMER CHAIN MOTION IN A SUPERIONIC SODIUM-POLY(ETHYLENE OXIDE) COMPLEX

S.G. Greenbaum and A.N. Shetty, Department of
Physics and Astronomy, Hunter College of CUNY,
New York, NY 10021

Accession For

1416	CRACI	X
1417	TIC	
1418		
1419		
1420		
1421		
1422		
1423		
1424		
1425		
1426		
1427		
1428		
1429		
1430		
1431		
1432		
1433		
1434		
1435		
1436		
1437		
1438		
1439		
1440		
1441		
1442		
1443		
1444		
1445		
1446		
1447		
1448		
1449		
1450		
1451		
1452		
1453		
1454		
1455		
1456		
1457		
1458		
1459		
1460		
1461		
1462		
1463		
1464		
1465		
1466		
1467		
1468		
1469		
1470		
1471		
1472		
1473		
1474		
1475		
1476		
1477		
1478		
1479		
1480		
1481		
1482		
1483		
1484		
1485		
1486		
1487		
1488		
1489		
1490		
1491		
1492		
1493		
1494		
1495		
1496		
1497		
1498		
1499		

A-1



A-1

Magnetic resonance measurements have been performed on the ion conducting complex poly(ethylene oxide), NaClO_4 . Low temperature ^{23}Na NMR spectra suggest a highly symmetric environment for the Na-ions as evidenced by the absence of quadrupole broadening. Proton spin-lattice relaxation measurements provide an estimate of $\sim 4 \times 10^{-10}$ sec for the polymer chain motional correlation time at $T = 69^\circ\text{C}$. Correlation times of tumbling paramagnetic probe molecule have been extracted from EPR spectra of ^{15}N -enriched TANOL-doped complex. Changes in polymer chain mobility above $T = 120^\circ\text{C}$ are inferred from the results and may be consistent with previous scanning calorimetry measurements.

The discovery of ion conducting complexes formed between alkali salts and poly(ethylene oxide) (PEO) by Wright and co-workers, (1-3) and subsequent investigations by Armand and co-workers (4,5) have generated a great deal of interest in this new class of materials. Because PEO and related complexes offer considerable promise as electrolytes in potentially superior solid state batteries, much of the research to date has focused on their ion transport properties (6-10).

In this paper we present magnetic resonance results for $\text{PEO}_{4.5}\text{NaClO}_4$ with particular emphasis on addressing the natures of both ionic and polymer chain motion in complex. Previous nuclear magnetic resonance (NMR) studies of lithium-salt association complexes with PEO (11) and related polymers (12,13) demonstrate a feature common to superionic solids - motional narrowing of ^7Li NMR lines in the temperature region of enhanced conductivity. As will be discussed, similar results are obtained for ^{23}Na in the present study. An important comment to be made regarding this observation is that the NMR measurements are also sensitive to local motional processes which do not necessarily contribute to the long range ion transport mechanisms that determine the material's conductivity.

Proton NMR can shed light on the dynamics of the polyether chains just as ^7Li or ^{23}Na NMR can for alkali ion motion. Another technique for probing molecular chain dynamics involves the use of paramagnetic impurity molecules such as 4-hydroxy-2,2,6,6-tetramethylpiperidine-1-N-1-oxyl (TANOL), in which tumbling correlation times of the impurities are extracted from electron paramagnetic resonance (EPR) spectra at various temperatures. (14) ^1H NMR and ^{15}N -enriched TANOL EPR data have also been obtained for $\text{PEO}_{4.5}\text{NaClO}_4$.

The samples were prepared by dissolving the appropriate amounts of PEO (MW- 5×10^6 ; Aldrich) and NaClO_4 (Aldrich) in methanol. The resulting solution was cast onto a Teflon plate and slowly evaporated at 40C. The films were then packed into sealed evacuated tubes for the resonance measurements, after being treated in a vacuum oven at 80C for 24 hours to drive off residual solvent or water. For the EPR measurements 0.05 weight percent perdeuterated ^{15}N -enriched (99.8%) TANOL (obtained from MSD Isotopes) was added to the solution prior to evaporation. NMR spectra and relaxation times were obtained with

a JEOL GX-400 spectrometer, and an IBM ER200 X-band spectrometer was utilized in conjunction with a Varian 4540 temperature controller for the EPR measurements.

The ^{23}Na NMR lineshape for $\text{PEO}_{4.5}\text{NaClO}_4$ at a resonance frequency of 105.8 MHz and $T = -85^\circ\text{C}$ is shown in Fig. 1. From linewidth and $\pi/2$ pulse-width considerations it can be concluded that there is no appreciable quadrupole broadening present. The absence of an observable quadrupole interaction indicates a highly symmetric environment for the rigid Na ions. Arguments based on conductometric studies of $\text{PEO} \cdot \text{KSCN}$ complex in methanol (15) and ^{23}Na NMR chemical shifts in Na-containing complexes (in solution) (16) suggest a tetrahedral configuration in which the cation is fourfold coordinated by the ether oxygens. (17) Although this model is consistent with the solid state measurements reported in this work, it is important to note that Berthier and co-workers have observed a quadrupole broadened ^{23}Na resonance line in $\text{PEO}_{10}\text{NaI}$. (18) These findings suggest a sensitivity of cation coordination to the stoichiometry of the complex.

The temperature dependence of the ^{23}Na linewidth (full-width at half-maximum, $\nu = 105.8$ MHz) is shown in Fig. 2. It is clear from that data that the "rigid-line" region corresponds to temperatures below -50°C . At higher temperatures motional narrowing occurs, the linewidth decreasing monotonically with increasing temperature up to the highest temperature measured (95°C). Motional narrowing of ^7Li NMR spectra has been reported for several Li salt-polymer complexes, (11-13) although the onset of the narrowing generally does not occur until -15°C or higher. For spin $I=1/2$ nuclei the narrowing process arises from motional averaging of the local field at the nuclear site due to the magnetic dipole-dipole interaction. Motional narrowing of quadrupole broadened spectra (for $I>1/2$) results principally from averaging of the electric field gradient (efg) at the nuclear site. The absence of a static efg deduced from the low temperature ^{23}Na spectrum in Fig. 1 suggests that efg fluctuations do not contribute to line-narrowing, thus yielding essentially the same result as for $I=1/2$ nuclei. It is possible, however, that additional insight into the ion hopping mechanism could be gained through ^{23}Na spin-lattice relaxation (T_1) measurements, due to the sensitivity of T_1 to efg fluctuations. (19)

← Fig 1

← Fig 2

Proton NMR spectra of PEO-alkali complexes are generally composed of two distinct features: a relatively narrow lorentzian component superimposed on a broad gaussian component.

(11,18,20) The broad component is identified with the relatively rigid CH_2 segments in the crystalline phase of the complex while the narrow line arises from mobile CH_2 segments in the elastometric phase. Proton T_1 data over the temperature range 0-100C is displayed in Fig.3. The bandwidth of the spectrometer employed in the measurements was limited to ~ 30 kHz by a combination of available rf power and digitizer speed designed for a nominally high-resolution instrument. Consequently ^1H spectra whose linewidths approached or exceeded this limit (below 0°C) were not utilized. The T_1 recovery profiles were found to be single-valued exponential with no resolvable differences between the broad and narrow components. From the local T_1 minimum occurring at $\sim 69\text{C}$ a polymer-chain motional correlation time $\tau = 10^{-10}$ s (at 69C) can be inferred (assuming that $\tau = 1$ at the T_1 minimum, where ω is the NMR frequency).

← Fig 3

In order to obtain additional information regarding the chain dynamics, EPR linewidth measurements of TANOL-doped $\text{PEO}_{0.5}\text{NaClO}_4$ were employed. It is important to note that because the probe molecules are not covalently bonded to the polymer chains, their rotational behavior provides only a qualitative measure of motion of the host polymer matrix in which the probes are imbedded. An interesting feature of the EPR spectra is that they do not reflect the coexistence of both crystalline (expected to yield "slow-tumbling") and elastometric (fast-tumbling) phases. A possible explanation for this may be related to different solubilities of TANOL in each phase that would tend to favor the segregation of the probe molecules in the elastomeric phase.

In the "fast-tumbling" region ($\lesssim 10^{-9}$ s) the ^1N EPR hyperfine component linewidths are related to the rotational correlation time τ of the probe molecule in a simple manner (14,21). The EPR first-derivative spectra are symmetric with respect to the baseline in this region. For $\text{PEO}_{0.5}\text{NaClO}_4$, the onset of fast-tumbling occurs at 72C, above which Kivelson's formula (22) for computing τ is applicable. The temperature dependence of the nitroxide tumbling correlation time is shown in Fig.4.

← Fig 4

The probe tumbling behavior appears to be characterized by two activation energies, $0.46 \pm .05$ eV for $T \leq 120$ C, and $0.13 \pm .08$ eV above this temperature. Differential scanning calorimetry (DSC) results for $\text{PEO}_{4.5}\text{NaClO}_4$ reveal the presence of a sharp thermal event in the vicinity of $T = 150$ C (23). The sharpness of the DSC feature suggests melting of the crystalline complex at $T \sim 150$ C, although progressive dissolution of the crystalline phase in the elastometric phase cannot be ruled out, as indicated by similar results obtained for $\text{PEO}_6\text{LiCF}_3\text{SO}_3$ (18). In either case it appears as though the abrupt drop in nitroxide probe rotational activation energy should be related to increased chain mobility above ~ 120 C which is also consistent with the DSC result. It is interesting to note that the probe tumbling correlation time at $T \sim 69$ C is about 7×10^{-10} s, which is close to the NMR-determined τ for the polymer chains ($\sim 4 \times 10^{-10}$ s) at that temperature.

Additional measurements (including ^{23}Na T_1) as a function of Na concentration are currently in progress.

Acknowledgements

The authors acknowledge Prof. Sook Lee of Hunter College for suggesting the EPR experiment and for enlightening discussions. Prof. Frank Landesberger of Rockefeller University is thanked for the use of his EPR facility for preliminary measurements, Prof. John Fontanella of the U.S. Naval Academy is acknowledged for providing useful information during the early stages of this work. This research was supported by grants from the Office of Naval Research, Research Corporation, and the City University of New York PSC-CUNY Research Award Program.

References

1. D.E. Fenton, J.M. Parker, P.V. Wright, Polymer **14**, 589 (1973).
2. P.V. Wright, Br. Polym. J. **7**, 319 (1975).
3. P.V. Wright, J. Polym. Sci.; Polymer Phys. **14**, 955 (1976).
4. M.B. Armand, J.M. Chabagno, M.J. Duclot, in Fast Ion Transport in Solids, J.N. Mundy, G.K. Shenoy, Eds., Pergamon Press, N.Y., 1979, p.131.
5. M.B. Armond, Solid State Ionics **9&10**, 745 (1983).
6. C.C. Lee, P.V. Wright, Polymer **23**, 681 (1982).
7. P.R. Sorensen, T. Jacobsen, Solid State Ionics **9&10**, 1147 (1983).
8. J.E. Weston, B.C.H. Steele, Solid State Ionics **7**, 75 (1982).
9. W.I. Archer, R.D. Armstrong, Electrochimica Acta **26**, 167 (1981).
10. A. Hooper, J.M. North, Solid State Ionics **9&10**, 1161 (1983).
11. F.L. Tanzella, W. Bailey, D. Frydrych, G.C. Farrington, H.S. Story, Solid State Ionics **5**, 681 (1981).
12. A. Killis, J.F. LeNest, A. Gandini, H. Cheradame, J.P. Cohen-Addad, Polymer Bulletin **6**, 351 (1982).
13. M.C. Wintersgill, J.J. Fontanella, J.P. Calame, S.G. Greenbaum, C.G. Andeen, J. Electrochem. Soc. **131**, 2208 (1984).
14. Spin-Labeling, Theory and Applications, L.J. Berliner, Ed., Academic Press, New York, 1979.
15. K. Ono, H. Konami, K. Murakami, J. Phys. Chem. **83**, 2665 (1979).
16. C. Detellier, P. Laszlo, Helv. Chim. Acta **49**, 1333 (1976).
17. B.L. Papke, M.A. Ratner, D.F. Shriver, J. Electrochem. Soc. **129**, 1694 (1982).
18. C. Berthier, W. Gorecki, M. Minier, M.B. Armand, J.M. Chabagno, F. Rigaud, Solid State Ionics **11**, 91 (1983).

19. J.L. Bjorkstam, M. Villa, Magnetic Resonance Review 6, 1 (1980).
20. S.G. Greenbaum, J.J. Fontanella, in Proceedings of Workshop on Relaxation in Disordered Systems, Blacksburg VA, 1983. K.L. Ngai, ed., U.S. Government Printing Office, in press.
21. B.J. Gaffney, C.H. Elbrecht, J.P.A. Scibilia, J. Magn. Reson. 44, 436 (1981).
22. Electron Spin Relaxation in Liquids, Muus, Atkins, ed., Plenum, London, 1972; p. 213.
23. J.J. Fontanella, unpublished.

Fig. 1. ^{23}Na NMR absorption lineshape at
 $T = -85^\circ\text{C}$, $\nu_0 = 105.8$ MHz in
 $\text{PEO}_{4.5}\text{NaClO}_4$.

Fig. 2. ^{23}Na full-width at half-maximum vs.
temperature ($^\circ\text{C}$) in $\text{PEO}_{4.5}\text{NaClO}_4$.

Fig. 3. ^1H spin-lattice relaxation time (T_1)
vs. reciprocal temperature in
 $\text{PEO}_{4.5}\text{NaClO}_4$.

Fig. 4. Temperature dependence of correlation
time for nitroxide radical tumbling
in $\text{PEO}_{4.5}\text{NaClO}_4$ doped with 0.05%
 ^{15}N -enriched TANOL.




Figure 1

Greenbaum, Shelly




Figure 2

Greenbaum et al.




Figure 3

Greenbaum, Shelly




Figure 4
Greenbaum, Slattery
(revised drawing)

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1		

ABSTRACTS DISTRIBUTION LIST, 359/627

Dr. Paul Delahay
Department of Chemistry
New York University
New York, New York 10003

Dr. P. J. Hendra
Department of Chemistry
University of Southampton
Southampton SO9 5NH
United Kingdom

Dr. T. Katan
Lockheed Missiles and
Space Co., Inc.
P.O. Box 504
Sunnyvale, California 94088

Dr. D. N. Bennion
Department of Chemical Engineering
Brigham Young University
Provo, Utah 84602

Mr. Joseph McCartney
Code 7121
Naval Ocean Systems Center
San Diego, California 92152

Dr. J. J. Auburn
Bell Laboratories
Murray Hill, New Jersey 07974

Dr. Joseph Singer, Code 302-1
NASA-Lewis
21000 Brookpark Road
Cleveland, Ohio 44135

Dr. P. P. Schmidt
Department of Chemistry
Oakland University
Rochester, Michigan 48063

Dr. H. Richtol
Chemistry Department
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. R. A. Marcus
Department of Chemistry
California Institute of Technology
Pasadena, California 91125

Dr. E. Yeager
Department of Chemistry
Case Western Reserve University
Cleveland, Ohio 44106

Dr. C. E. Mueller
The Electrochemistry Branch
Naval Surface Weapons Center
White Oak Laboratory
Silver Spring, Maryland 20910

Dr. Sam Perone
Chemistry & Materials
Science Department
Lawrence Livermore National Laboratory
Livermore, California 94550

Dr. Royce W. Murray
Department of Chemistry
University of North Carolina
Chapel Hill, North Carolina 27514

Dr. B. Brummer
EIC Incorporated
111 Downey Street
Norwood, Massachusetts 02062

Dr. Adam Heller
Bell Laboratories
Murray Hill, New Jersey 07974

Electrochimica Corporation
Attn: Technical Library
2485 Charleston Road
Mountain View, California 94040

Library
Duracell, Inc.
Burlington, Massachusetts 01803

Dr. A. B. Ellis
Chemistry Department
University of Wisconsin
Madison, Wisconsin 53706

Dr. Manfred Breiter
Institut für Technische Elektrochemie
Technischen Universität Wien
9 Getreidemarkt, 1160 Wien
AUSTRIA

ABSTRACTS DISTRIBUTION LIST, 359/627

Dr. M. Wrighton
Chemistry Department
Massachusetts Institute
of Technology
Cambridge, Massachusetts 02139

Dr. B. Stanley Pons
Department of Chemistry
University of Utah
Salt Lake City, Utah 84112

Donald E. Mains
Naval Weapons Support Center
Electrochemical Power Sources Division
Crane, Indiana 47522

S. Ruby
DOE (STOR)
M.S. 6B025 Forrestal Bldg.
Washington, D.C. 20595

Dr. A. J. Bard
Department of Chemistry
University of Texas
Austin, Texas 78712

Dr. Janet Osteryoung
Department of Chemistry
State University of New York
Buffalo, New York 14214

Dr. Donald W. Ernst
Naval Surface Weapons Center
Code R-33
White Oak Laboratory
Silver Spring, Maryland 20910

Mr. James R. Moden
Naval Underwater Systems Center
Code 3632
Newport, Rhode Island 02840

Dr. Bernard Spielvogel
U.S. Army Research Office
P.O. Box 12211
Research Triangle Park, NC 27709

Dr. Aaron Fletcher
Naval Weapons Center
Code 3852
China Lake, California 93555

Dr. M. M. Nicholson
Electronics Research Center
Rockwell International
3370 Miraloma Avenue
Anaheim, California

Dr. Michael J. Weaver
Department of Chemistry
Purdue University
West Lafayette, Indiana 47907

Dr. R. David Rauh
EIC Laboratories, Inc.
111 Downey Street
Norwood, Massachusetts 02062

Dr. Aaron Wold
Department of Chemistry
Brown University
Providence, Rhode Island 02192

Dr. Martin Fleischmann
Department of Chemistry
University of Southampton
Southampton SO9 5NH ENGLAND

Dr. R. A. Osteryoung
Department of Chemistry
State University of New York
Buffalo, New York 14214

Dr. Denton Elliott
Air Force Office of Scientific
Research
Bolling AFB
Washington, D.C. 20332

Dr. R. Nowak
Naval Research Laboratory
Code 6170
Washington, D.C. 20375

Dr. D. F. Shriver
Department of Chemistry
Northwestern University
Evanston, Illinois 60201

Dr. Boris Cahan
Department of Chemistry
Case Western Reserve University
Cleveland, Ohio 44106

ABSTRACTS DISTRIBUTION LIST, 359/627

Dr. David Aikens
Chemistry Department
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. A. B. P. Lever
Chemistry Department
York University
Downsview, Ontario M3J1P3

Dr. Stanislaw Szpak
Naval Ocean Systems Center
Code 6343, Bayside
San Diego, California 95152

Dr. Gregory Farrington
Department of Materials Science
and Engineering
University of Pennsylvania
Philadelphia, Pennsylvania 19104

M. L. Robertson
Manager, Electrochemical
and Power Sources Division
Naval Weapons Support Center
Crane, Indiana 47522

Dr. T. Marks
Department of Chemistry
Northwestern University
Evanston, Illinois 60201

Dr. Micha Tomkiewicz
Department of Physics
Brooklyn College
Brooklyn, New York 11210

Dr. Lesser Blum
Department of Physics
University of Puerto Rico
Rio Piedras, Puerto Rico 00931

Dr. Joseph Gordon, II
IBM Corporation
K33/281
5600 Cottle Road
San Jose, California 95193

Dr. Hector D. Abruna
Department of Chemistry
Cornell University
Ithaca, New York 14853

Dr. D. H. Whitmore
Department of Materials Science
Northwestern University
Evanston, Illinois 60201

Dr. Alan Bewick
Department of Chemistry
The University of Southampton
Southampton, SO9 5NH ENGLAND

Dr. E. Anderson
NAVSEA-56Z33 NC #4
2541 Jefferson Davis Highway
Arlington, Virginia 20362

Dr. Bruce Dunn
Department of Engineering &
Applied Science
University of California
Los Angeles, California 90024

Dr. Elton Cairns
Energy & Environment Division
Lawrence Berkeley Laboratory
University of California
Berkeley, California 94720

Dr. D. Cipris
Allied Corporation
P.O. Box 3000R
Morristown, New Jersey 07960

Dr. M. Philpott
IBM Corporation
5600 Cottle Road
San Jose, California 95193

Dr. Donald Sandstrom
Boeing Aerospace Co.
P.O. Box 3999
Seattle, Washington 98124

Dr. Carl Kannewurf
Department of Electrical Engineering
and Computer Science
Northwestern University
Evanston, Illinois 60201

Dr. Richard Pollard
Department of Chemical Engineering
University of Houston
4800 Calhoun Blvd.
Houston, Texas 77004

DL/413/83/01
359/413-2

ABSTRACTS DISTRIBUTION LIST, 359/627

Dr. Robert Somoano
Jet Propulsion Laboratory
California Institute of Technology
Pasadena, California 91103

Dr. Johann A. Joebstl
USA Mobility Equipment R&D Command
DRDME-EC
Fort Belvoir, Virginia 22060

Dr. Judith H. Ambrus
NASA Headquarters
M.S. RTS-6
Washington, D.C. 20546

Dr. Albert R. Landgrebe
U.S. Department of Energy
M.S. 6B025 Forrestal Building
Washington, D.C. 20595

Dr. J. J. Brophy
Department of Physics
University of Utah
Salt Lake City, Utah 84112

Dr. Charles Martin
Department of Chemistry
Texas A&M University
College Station, Texas 77843

Dr. H. Tachikawa
Department of Chemistry
Jackson State University
Jackson, Mississippi 39217

Dr. Theodore Beck
Electrochemical Technology Corp.
3935 Leary Way N.W.
Seattle, Washington 98107

Dr. Farrell Lytle
Boeing Engineering and
Construction Engineers
P.O. Box 3707
Seattle, Washington 98124

Dr. Robert Gotscholl
U.S. Department of Energy
MS G-226
Washington, D.C. 20545

Dr. Edward Fletcher
Department of Mechanical Engineering
University of Minnesota
Minneapolis, Minnesota 55455

Dr. John Fontanella
Department of Physics
U.S. Naval Academy
Annapolis, Maryland 21402

Dr. Martha Greenblatt
Department of Chemistry
Rutgers University
New Brunswick, New Jersey 08903

Dr. John Wasson
Syntheco, Inc.
Rte 6 - Industrial Pike Road
Gastonia, North Carolina 28052

Dr. Walter Roth
Department of Physics
State University of New York
Albany, New York 12222

Dr. Anthony Sammells
Eltron Research Inc.
4260 Westbrook Drive, Suite 111
Aurora, Illinois 60505

Dr. W. M. Risen
Department of Chemistry
Brown University
Providence, Rhode Island 02192

Dr. C. A. Angell
Department of Chemistry
Purdue University
West Lafayette, Indiana 47907

Dr. Thomas Davis
Polymer Science and Standards
Division
National Bureau of Standards
Washington, D.C. 20234

Ms. Wendy Parkhurst
Naval Surface Weapons Center R-33
Silver Spring, Maryland 20910

END

FILMED

5-85

DTIC